

Local Agency Programs
Hot Mix Asphalt (HMA) Selection Guidelines

Rev: 06/14/2016 - FHWA Approval: 08/29/2016

The following guidelines have been developed at the request of Local Agency Engineers for use on Local Agency projects. These guidelines have been reviewed and approved by the County Road Association of Michigan Engineering Committee. Previous experience and performance shall permit variations from these guidelines as per Section D. Alternative Mixes.

A. HMA Mixture Type and Binder Selection

Selection is based on present day two-way commercial ADT. The commercial ADT ranges for each of the mixture types have taken into account an assumed future traffic growth rate.

Com. ADT.	Com. ADT 0-300	Com. ADT 301-700	Com. ADT 701-1000	Com. ADT 1001-3400	Com. ADT 3401- 9999
Mixture Type					
Top	LVSP or 13A, 36A	4C 5E1/4E1	5E3, or 4E3	5E10, or 4E10	5E30, or 5E10
Leveling	LVSP or 13A	3C 4E1	4E3	4E10	4E30
Base	13A / 3C	2C / 3C	3E3	3E10	3E30
Binder Grades by Region					
Superior	PG 58-34	PG 58-34	PG 58-34	PG 58-34	
Metro	PG 58-22	PG 64-22	PG 64-22	PG 64-22	PG 70-22P
All Other	PG 58-28	PG64-28	PG-64-28	PG64-28	PG70-28P

Note 1: If the designer wishes to reduce the target air voids on projects to 3.5%, a note needs to be added to the plans on the HMA Application Table stating that the air voids have been changed to 3.5% for that particular project for top and leveling courses. For mixtures meeting the definition of base course, field regress air void content to 3.0 percent with liquid asphalt cement unless specified otherwise on HMA application estimate.

Note 2: The mixture type in each traffic category listed in the above table is specifically designed to perform under their respective Commercial ADT. Selecting a mixture type that is specifically designed for a higher Commercial ADT than the project being designed may adversely affect performance.

Note 3: One course overlays on composite pavements where the prevention of cold temperature related thermal cracking is not as much of a concern, the cold temperature number of the PG binder may be decreased by one grade to help reduce costs.

Example: For a one course overlay in the Superior Region on a composite project, the recommended PG binder would be a PG58-28 instead of a PG58-34.

Note 4. To address traffic areas that are more susceptible to rutting early in pavements life such as signalized intersections and other areas of stop/start traffic use the pay item entitled **High Stress Hot Mix Asphalt Mixture**. The difference between the High Stress HMA Mixture and the typical HMA pay item is the Performance Graded binder. For High Stress Mixtures, increase the high temperature binder by one grade and add the polymer. The increase in the high temperature number results in an asphalt binder with improved high temperature stiffness or rutting resistance for both the leveling and top course.

Example: For a high stress application for a mixture type 5E3 placed in an intersection the recommended binder grade would be a PG70-28P instead of a PG64-28. Following are the recommend guides for the proper application of the Special Provision for High Stress Hot Mix Asphalt Mixture:

- a. Use this pay item 1000 feet on either side of the center of signalized intersections and other areas where stop/start traffic occurs on the mainline (for quantity calculations use 1100 feet).
- b. There are cases where the signalized intersections are spaced 1 mile or less over the entire length of the project. When this occurs, specify the High Stress HMA Mixture pay item for the entire length.
- c. All HMA approaches that are adjacent to the High Stress HMA Mixture areas should be specified using this pay item.
- d. Use of the Pay Item: High Stress HMA (mix), should not be used unless it is to be distinguished from the same mix with a different PG grade.

B. Application Rates

HMA application rates shown in the table below are the required minimum and maximum rates for each of the specific mixtures. Pavement designs requiring a HMA greater than the recommended maximum will require multiple lifts of the leveling and/or base mixes.

Mixture Type	Marshall Mixture					Superpave Mixture				
	36A	13A	2C	3C	4C	LVSP	3E_	4E1	4E3+	5E_
Min. #/syd	110	165	350	220	165	165 Top or Leveling	330	165	220	165
Max. #/syd	165	275	500	330	275	220 Top 250 Leveling	410	330	275	220

Note 1: Application rate of 110 #/Syd. Per 1 inch thickness.

Note 2: When shoulders of 8 ft. or greater are being paved as a separate operation on a project, the following note should be added to the plans near the HMA Application Table; “For shoulders only, the mix design and/or JMF target value for Air Voids are to be adjusted to 2.5 percent.” If it is not known whether the shoulders will be placed as a separate paving operation, the note should be added.

C: Aggregate Wear Index (All Projects)

Aggregate Wear Index (AWI) is required for all aggregates used in HMA top course mixtures. The following table identifies the required minimum AWI, based on the present average daily traffic (vehicular and commercial) per lane (ADT/Lane):

ADT/Lane	Minimum AWI
<100	None
100 - 2000	220
>2000	260

D: Alternative Mixes

These guidelines provide for the selection of Hot Mixed Asphalt (HMA) and application rates utilizing the Superpave mix design system along with the Marshall Mix design system. The substitution of another HMA mixture type other than the recommended mixture is acceptable if it has demonstrated to perform under similar traffic conditions. If a local agency desires to use an HMA mixture or grade of binder other than what is contained within this guide, they must submit the change in writing. The letter or email must include the alternate mix design, the justification/reason for the change, and a statement that they accept responsibility for the outcome of the performance of the mix design that is used in lieu of the recommended mixture.